Braskem

FPT300F

Homopol mer Pol prop lene

- Good Mold Release, Excellent Part Finish (Low Bloom)
- Suggested Uses Include Housewares, Caps and Closures, Mugs / Cups, Thin-Walled Containers

Propert	Units	T pical Value	Test Metho
Nominal Melt Flow Rate (230°C/2.16kg)	g/10 min	30	ASTM D1238
Tensile Strength at Yield (2 in/min, 50 mm/min)	psi MPa	4,800 33	ASTM D638
Elongation at Yield (2 in/min, 50 mm/min)	%	10	ASTM D638
Flexural Modulus (0.05 in/min, 1.3 mm/min, 1% secant)	psi MPa	200,000 1,379	ASTM D790A
Notched Izod Impact Strength at 23°C	ft-lbs/in J/m	0.7 37	ASTM D256A
Rockwell Hardness	R	104	ASTM D785

Information contained herein is considered accurate to our best knowledge. It is offered for your consideration and investigation, and is not to be construed as a representation or warranty, expressed or implied, for which Braskem assumes legal responsibility. Our warranties are limited to those expressly stated in formal contracts or in conditions of sale on our invoices and order acceptances. Conditions and methods of use vary and are beyond the control of Braskem. Braskem, therefore, disclaims any liability incurred as a result of the use of its products in accordance with the data contained herein. No information herein shall be construed as an offer of indemnity for infringement or as a recommendation to use these products in such a manner as to infringe any patent, domestic or foreign.

For cautions an other information relating to han ling of

550 Technology Drive

Revision Date: Monday, March 23, 2009

an e posure to this pro uct, please see material safet ata sheet co e number C4001 publishe b Braskem.

Pittsburgh, PA 15219 1-800-223-8871

www.braskem.com



MOLD-RITE PLASTICS LLC. I Plant Street P.O. Box 160 Plattsburgh NY 12901 (518)561-1812 https://www.mrpcap.com

Product Data Sheet

MRPWH01 White

Product Description

This specification designated by Mold-Rite Plastics covers all colorants that meet the typical value data listed below.

Regulatory Compliance

FDA – Title 21 CFR Section 170-199 for Food & Drug Contact RoHS Compliant CONEG/Heavy Metal Compliant Proposition 65 Compliant

Typical Properties	Typical Value		
Density	.90		
Melt Index	30		
Pellets	Standard		
Recommended Let Down Ratio	50:1		
Carrier Resin	PP		
Estimated Heat Stability	450-500 °F		
Visual Evaluation	Excellent		
Additives	None		
DE Tolerance	< 2.00		

For further regulatory information, contact Mold-Rite Plastics customer service or sales department.

Notes: These are typical properties not to be construed as specifications. Mold-Rite Plastics reserves that right to include any other colorant that meets that above data values and regulatory requirements.

This product data sheet covers multiple colorant formulations that meet the above typical data values and regulatory requirements. All listed formulas have similar physical, chemical and processing properties. Listed known formulas; Polymer Concentrates – 10536, Penn Color 60W5221

All results were obtained from manufacturer product data sheets (where applicable). The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of Mold-Rite Plastics products must be guided by the users own methods for selection of proper formulation. Mold-Rite Plastics disclaims any responsibility for misuse or miss application of its products. Mold-Rite Plastics liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option for replacement not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.



Product Data Sheet

MRP Description:(A01)MRPLN04.020 FOAM R SFYP

MRPLN04 - Universal Heat Seal Foam Liner

Product Description

This product is a 1 piece universal heat seal consisting of foam backing, paper, alu	minum foil and heat seal layer
This specification, designated by Mold-Rite Plastics, covers all liners that meet the t	
Polystyrene Foam	,
Paper	
Aluminum Foil	
Heat Seal Couting	

Regulatory Compliance

FDA. Title 21 CFR Section 177.1210 (Closure with Sealing Gaskets for Food Containers, RoHS Compliant CONEG/Heavy Metal Compliant Proposition 65 Compliant


Typical Properties	Typical Value		
Overall Thickness	.024 +/- 10%		
Drug Master File	16574		
Printed	R SFYP		
Oxygen Transmission	Essentially Zero		
Water Vapor Transmission	Essentially Zero		


For further regulatory information, contact Mold-Rite Plastics customer service or sales department.


Notes: These are typical properties not to be construed as specifications. Mold-Rite Plastics reserves that right to include any other liner that meets that above data values and regulatory requirements,

This product data sheet covers multiple liners that meet the above typical data values and regulatory requirements. All listed liners have similar physical, chemical and processing properties. Listed known liners: HS035, HS 035N, HS205, FS5-8, HSS-5.6

All results were obtained from manufacturer product data sheets (where applicable). The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of Mold-Rite Plastics products must be guided by the users own methods for selection of proper formulation. Mold-Rite Plastics disclaims any responsibility for misuse or miss application of its products. Mold-Rite Plastics liability and customer's exclusive remody for any claims arising out of sales of its products are expressly limited at customer option for replacement not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.







THREAD DETAIL INFORMATION:
6 THREADS PER INCH, 0.167" PITCH

REFERENCE	TOLERANCE	UNITS	DIMENSION
E	±0.010 [0.25]	in [mm]	1.656 [42.06]
Т	±0.010 [0.25]	in [mm]	1.752 [44.50]
Н	±0.010 [0.25]	in [mm]	0.390 [9.91]
OD	±0.012 [0.30]	in [mm]	1.865 [47.37]
OAH	±0.010 [0.25]	in [mm]	0.445 [11.30]
PART WEIGHT	± 0.50	g	3.90

STATIC TORQUE RECOMMENDATION 17-27 in-lbs THIS REQUIREMENT MAY VARY DEPENDING UPON BOTTLE MATERIAL, NECK FINISH, AND CAPPING EQUIPMENT

THE CLOSURE DIMENSIONS
DEPICTED ARE THOSE WHICH HAVE GENERALLY BEEN FOUND TO BE FUNCTIONAL BASED ON INDUSTRY EXPERIENCE BECAUSE OF VARIABILITY IN GLASS AND PLASTIC CONTAINER FINISHES, EACH CLOSURE/FINISH SYSTEM SHOULD BE INDIVIDUALLY EVALUATED AND TESTED TO ENSURE IT MEETS APPLICABLE PERFORMANCE CRITERIA, SEE QUALITY ASSURANCE SPECIFICATIONS FOR ADDITIONAL INFORMATION,

MOLD-RITE, WEATHERCHEM AND STULL TECHNOLOGIES RESERVES THE RIGHT TO REVISE ANY OR ALL SPECIFICATIONS AND REQUIREMENTS,

DRAWING TYPE: CUSTOMER

REPLACES DRAWINGS: c-3010		DIMENSIONS EI INDICATE R DIMENSIONS AND LIMITS ARE E	EFERENCE NO TOLERANCE
TC	LERANCES UNLESS	OTHERWISE SPECIF	IED
DIMENSION (inches)	TOLERANCE	DIMENSION (mm)	TOLERANCE
0-0.787	±0,006	0-20	±0.152
 0,788-1,181	±0,008	21-30	±0.203
1.182-2,756	±0,012	31-70	±0.305
2.757-3,937	±0.016	71-100	±0.406
3,938-5,096	±0,020	101-150	±0.508
5.097-7.874	±0,024	151-200	±0.610
7.875-9.843	±0.032	201-250	±0.813
	AMOULADIO	LEDANOE . O.	

PROPRIETARY AND CONFIDENTIAL


THIS DRAWING IS PROTECTED BY COPYRIGHT AND CONTAINS INFORMATION PROPRIETARY TO MOLD-RITE, WEATHERCHEM AND STULL TECHNOLOGIES. ANY REPRODUCTION, DISCLOSURE, OR USE OF ITS CONTENTS OR ANY PART THEREOF IS EXPRESSLY PROHIBITED EXCEPT AS MOLD-RITE, WEATHERCHEM AND STULL TECHNOLOGIES OTHERWISE MAY AGREE IN WRITING




Innovative · Reliable · Responsive

							3 H
	THIRD ANGLE PROJECTION	1	CODE	45-400 CT CLOSURE RS (Ribbed Side - Smooth Top		o)	
	SOLIDWORKS			DRAWING NUM	CQA - 1	0301	
_	DRAWN 8Y,	JDM	6/3/2016	MATERIAL	POLYPRO	PYLENE	
7	ENG APPR.	BDG	8/17/2017	MODEL NUMBE	R: PM 10297 4	5-400 CT	
М	QA APPR,	REL	09/05/2017	SCALE 1:1	SHEET SIZE 8,5in*11in	SHEET 1 of 3	REV.NP 00.AC
- 5			6		7		8

				REVI	SIONS					
DATE	REV.	N/P	PRODUCT DRAWING REQUEST		DESCRI	PTION		***	ENG	DRW
6/3/2016	00	AA	PDR 16-025		AWING FORM FOR REVISIO			-3010	JDM	JDM
5/5/2017	00	AB		ADD	ED GATE LO	CATION (OPTION		JDM	JDM
7/27/17	00	AC	PDR 17-035		OD TOLERAN GHT BASED (BDG	DAS





152 EQUALLY SPACED RIBS DETAIL RIBS SCALE 4:1

MOLD NUMBER	GATE LOCATION
45001	SIDE
45002	SIDE
45003	SIDE
45005	SIDE
45007	SIDE
45011	TOP CENTER


THE CLOSURE DIMENSIONS
DEPICTED ARE THOSE WHICH HAVE GENERALLY BEEN FOUND TO BE FUNCTIONAL BASED ON INDUSTRY
EXPERIENCE BECAUSE OF VARIABILITY IN GLASS AND PLASTIC CONTAINER FINISHES, EACH CLOSURE/FINISH SYSTEM SHOULD BE INDIVIDUALLY EVALUATED AND TESTED TO ENSURE IT MEETS APPLICABLE PERFORMANCE CRITERIA, SEE QUALITY ASSURANCE SPECIFICATIONS FOR ADDITIONAL INFORMATION.


MOLD-RITE, WEATHERCHEM AND STULL TECHNOLOGIES RESERVES THE RIGHT TO REVISE ANY OR ALL SPECIFICATIONS AND REQUIREMENTS.

DRAWING TYP	E: CUSTO	MER	
REFERENCES: 45001, 45002, 45003, 45005, 45007, 45011		INDICATE F DIMENSIONS AND	NCLOSED IN () REFERENCE) NO TOLERANCE STABLISHED
T	OLERANCES UNLESS	OTHERWISE SPECIF	IED
DIMENSION (inches)	TOLERANCE	DIMENSION (mm)	TOLERANCE
0-0.787	±0.006	0-20	±0.152
0,788-1,181	±0.008	21-30	±0.203
1.182-2.756	±0.012	31-70	±0.305
2.757-3.937	±0,016	71-100	±0.406
3,938-5,096	±0.020	101-150	±0.508
5,097-7,874	±0,024	151-200	±0.610
7.875-9.843	±0.032	201-250	±0,813
	ANGULAR TO	LERANCE ± 2°	
F	PROPRIETARY AND	CONFIDENTIAL	
THIS DRAWING IS F	ROTECTED BY COP	YRIGHT AND CONTAIL	NS INFORMATION
ANY REPRODUCTION	MULU-KITE, WEATHI	ERCHEM AND STULL USE OF ITS CONTEN	ITECHNOLOGIES.
THEREOF IS EXPRE	SSLY PROHIBITED E	XCEPT AS MOLD-RITE	E. WEATHERCHEM
AND STULL T	ECHNOLOGIES OTHE	RWISE MAY AGREE	IN WRITING
,		4	5

	RP///
NOLD-	RITE PLASTICS

-							63	_
	THIRD ANGLE PROJECTION		DISTRIBUTION CODE		DRAWING NAME 45-400 CT CLOSURE RS (Ribbed Side - Smooth Top)			
	SOLICHTERKS	T Soldowerks		CQA - 10301				
-	DRAWN BY.	DRAWN BY. JDM 6/3/2016		MATERIAL	POLYPROPYLENE			ĺ
	ENG APPR.	BDG	8/17/2017	MÖDEL NUMBER: PM 10297 45-400 CT				
4	QA APPR.	REL	09/05/2017	SCALE 1:1	SHEET SIZE 8 .5 X 11	SHEET 2 of 3	REV,NP 00,AC	ļ
5			6	i i	7	2010	8 00.710	





SECTION C-C SCALE 1:1

REFERENCE	TOLERANCE	UNITS	DIMENSION
E	± 0.017 [0.43]	in [mm]	1.631 [41.43]
Т	± 0.017 [0.43]	in [mm]	1.725 [43.82]
I	MINIMUM	in [mm]	1.525 [38.74]
S	± 0.015 [0.38]	in [mm]	0.046 [1.17]
H	± 0.015 [0.38]	in [mm]	0.415 [10.54]
TPI			6
PITCH		in [mm]	0.167 [4.24]

NOTE: THE NOMINAL ORIENTATION ILLUSTRATED IS BASED ON NOMINAL DIMENSIONS OF BOTH THE CLOSURE AND THE RECOMMENDED NECK FINISH, FOR EXACT ORIENTATION EACH BOTTLE SHOULD BE EVALUATED ON A CASE BY CASE BASIS.

THE CLOSURE DIMENSIONS
DEPICTED ARE THOSE WHICH HAVE GENERALLY BEEN
FOUND TO BE FUNCTIONAL BASED ON INDUSTRY
EXPERIENCE BECAUSE OF VARIABILITY IN GLASS AND
PLASTIC CONTAINER FINISHES, EACH CLOSURE/FINISH
SYSTEM SHOULD BE INDIVIDUALLY EVALUATED AND
TESTED TO ENSURE IT MEETS APPLICABLE
PERFORMANCE CRITERIA. SEE QUALITY ASSURANCE
SPECIFICATIONS FOR ADDITIONAL INFORMATION.

MOLD-RITE, WEATHERCHEM AND STULL TECHNOLOGIES RESERVES THE RIGHT TO REVISE ANY OR ALL SPECIFICATIONS AND REQUIREMENTS.

DRAWING TYPE:	CUSTOMER
---------------	----------

DIMENSIONS ENCLOSED IN () INDICATE REFERENCE DIMENSIONS AND NO TOLERANCE LIMITS ARE ESTABLISHED

TOLERANCES UNLESS OTHERWISE SPECIFIED						
DIMENSION (inches)	TOLERANCE	DIMENSION (mm)	TOLERANCE			
0-0.787	±0.006	0-20	±0.152			
0.788-1.181	±0.008	21-30	±0.203			
1.182-2.756	±0.012	31-70	±0.305			
2,757-3,937	±0.016	71-100	±0.406			
3,938-5,096	±0,020	101-150	±0.508			
5,097-7,874	±0.024	151-200	±0.610			
7.875-9.843	±0,032	201-250	±0,813			
	ANGULAR TO	LERANCE ± 2°				
PROPRIETARY AND CONFIDENTIAL						

THIS DRAWING IS PROTECTED BY COPYRIGHT AND CONTAINS INFORMATION PROPRIETARY TO MOLD-RITE, WEATHERCHEM AND STULL TECHNOLOGIES. ANY REPRODUCTION, DISCLOSURE, OR USE OF ITS CONTENTS OR ANY PART THEREOF IS EXPRESSLY PROHIBITED EXCEPT AS MOLD-RITE, WEATHERCHEM AND STULL TECHNOLOGIES OTHERWISE MAY AGREE IN WRITING



	THIRD ANGLE PROJECTION SULLIWUSKS		STRIBUTION CODE			IISH	
	DRAWN BY. JDM 6/3/2016		MATERIAL				
	ENG APPR,	BDG	8/17/2017	MODEL NUMBER:			
1	QA APPR.	REL	09/05/2017	SCALE 1:2	SHEET SIZE 8 .5 X 11	SHEET 3 of 3	REV.N/P 00.AC